

Utilisation of Cassava Starch Edible Films containing Salicylic Acid on Papaya (*Carica papaya L.*) Preservation

Castro, Marlon¹; Mantuano, María-Isabel¹; Coloma, José-Luis¹; Santacruz, Stalin¹

¹ Universidad Laica Eloy Alfaro de Manabí, Avenida Circunvalación s/n, Manta, Ecuador. P.O. Box 13-05-2732

Abstract: In the present work papaya coated with edible films based either on chitosan or cassava starch was investigated. Film forming solutions were prepared with either 1 % (w/v) chitosan or 0,5 % (w/v) cassava starch. Salicylic acid (2 mmol/L) or a mixture of thymol (0,5 % w/v) and cinnamaldehyde (0,5 % w/v) were added to the starch film forming solution. Papayas were stored for 28 days at 11 °C and relative humidity (RH) between 70 and 80 %, followed by a maturation step of 4 days at 25 °C and 60 % RH. Papayas were analysed on weight loss, firmness, soluble solids, acidity, maturity index and disease severity every week. Uncoated papayas showed slight differences on weight loss compared to coated samples up to the third week of storage. No differences between acidity and soluble solids were found among the samples along the whole storage time. Uncoated samples showed a higher maturity index after the first week compared to coated samples whereas no difference was observed among coated papayas along the whole storage time. Uncoated samples showed a higher disease severity than samples coated with chitosan or salicylic acid up to the third week of storage, afterwards, the three samples showed similar results. The use of films based on cassava starch together with salicylic acid is a promising tool to preserve Hawaii papaya at refrigeration conditions.

Keywords: papaya, edible film, cassava starch, salicylic acid

Utilización de Películas Comestibles de Almidón de Yuca y Ácido Salicílico en la Conservación de Papaya (*Carica papaya L.*)

Resumen: En el presente trabajo se estudió recubrimientos comestibles a base de quitosano y almidón de yuca en papaya. Soluciones de recubrimiento se prepararon con 1% (w / v) quitosano o 0,5% (w / v) de almidón de yuca. El ácido salicílico (2 mmol / L) o una mezcla de timol (0,5% w / v) y cinamaldehído (0,5% w / v) se añadieron a la solución formadora de película de almidón. Papayas se almacenaron durante 28 días a 11 ° C y la humedad relativa (RH) entre 70 y 80%, seguido de una etapa de maduración de 4 días a 25 ° C y 60% RH. Las papayas fueron analizadas en la pérdida de peso, firmeza, sólidos solubles, acidez, índice de madurez y la gravedad de la enfermedad cada semana. Papayas no recubiertas mostraron pequeñas diferencias en la pérdida de peso en comparación con muestras recubiertas hasta la tercera semana de almacenamiento. No se encontraron diferencias entre la acidez y sólidos solubles entre las muestras a lo largo de todo el tiempo de almacenamiento. Muestras no recubiertas mostraron un índice de madurez superior después de la primera semana en comparación con las muestras recubiertas, mientras que no se observó diferencia entre papayas revestidas a lo largo de todo el tiempo de almacenamiento. Muestras no recubiertas mostraron una gravedad de la enfermedad mayor que las muestras recubiertas con quitosano o ácido salicílico hasta la tercera semana de almacenamiento, después, las tres muestras mostraron resultados similares. El uso de películas a base de almidón de yuca junto con el ácido salicílico es una herramienta prometedora para preservar papaya Hawaiana en condiciones de refrigeración.

Palabras clave: papaya, película comestible, almidón de yuca, ácido salicílico.

1. INTRODUCTION

Papaya is a climacteric fruit characterised by a short shelf life time. Therefore, papaya is harvested in a physiological maturity stage that guarantees its commercialisation. A major demand for papaya will keep an upward production trend in the next decade (OECD-FAO, 2015); therefore new post-

harvesting techniques or an improvement of the already in use is needed.

Edible films alone or carrying functional compounds, e.g. antimicrobial or antioxidant, have been employed to improve the quality of food (Vargas et al., 2008). The most common polymers on formulation of edible films are proteins,

polysaccharides and lipids, which are used alone or combined (Vargas et al., 2008). Starch is an important polysaccharide used in the formulation of biodegradable films (Chiumarelli et al., 2010). Among starches, cassava starch has been widely used on the formulation of edible films thanks to its availability and relative low price (Souza et al., 2012; Chivrac et al., 2010). Bezerra de Aquino et al. (2015) studied the use of cassava starch together with chitosan on guavas whereas Chiumarelli and Hubinger (2012) worked with films based on cassava starch and carnauba wax on apple slices. However no studies of the use of edible films based on cassava starch for papaya (*Carica papaya L.*) preservation have been developed.

Chitosan is obtained from chitin by deacetylation in an alkaline media (Abdou et al., 2007). Chitosan is a copolymer consisting of β -(1-4)-2-acetamido-D-glucose and β -(1-4)-2-amino-D-glucose units. The potential of chitosan as a food preservative of natural origin has been widely reported on basis of in vitro trials as well as through direct application on real complex matrix foods (Durango et al., 2006; Ribeiro et al., 2007). Edible film based on chitosan form a mechanical barrier against fungi (Meng et al., 2008).

Salicylic acid is the 2-hydroxybenzoic acid. It has antimicrobial and antifungal properties (El-Mougy, 2002). Salicylic acid is a resistance inducer and has been tested in fruits and flowers (Yao and Tian, 2005). It is a regulator of vegetal growth involved in the systematic resistance to pathogens (Kessmann et al., 1994) and in the biosynthesis and ethylene action (Raskin, 1992). Therefore, it can be considered an antagonist to ethylene, the main phytohormone of fruit maturation (Cia et al., 2007). Salicylic acid has been used to alleviate chilling injuries of cucumber and pomegranates (Zhang et al., 2015). However no studies on the effect of salicylic acid on the shelf life of papaya (*Carica papaya L.*) have been done.

Essential oils are hydrophobic substances with antimicrobial and antioxidant properties. They are normally used as natural preservative in the food industry. The antimicrobial activity is linked to the presence of terpenoids and phenolic compounds (Burt, 2004). Several studies have used essential oils from different sources to inhibit or delay the growth of pathogenic microorganisms (Burt, 2004; Raybaudi et al., 2006). Cinnamon essential oil is recognized as safe (GRAS) for human consumption and is normally used in food formulations, where it fits with desirable sensory characteristics. Cinnamaldehyde is one of the compounds of cinnamon oil and exhibits pronounced antimicrobial properties (Pauli and Schilcher, 2010). Thymol, carvacrol and eugenol are major components in essential oils derived from thyme, oregano and clove bud. They are among the most-studied essential oil compounds (Chinou et al., 2009; Pan et al., 2014) due to their excellent activities against bacteria, viruses, fungi, parasites, and insects (Burt, 2004). The antimicrobial activity of cinnamaldehyde and thymol incorporated into films has been investigated (De Souza et al., 2014; Mastromatteo et al., 2009). However, the use of cinnamaldehyde together with thymol on papaya preservation has not been studied before.

In the present work, preservation of Hawaii papaya was investigated by using edible films based on cassava starch together with salicylic acid or a mixture of cinnamaldehyde and thymol as antimicrobial agents. A comparison between cassava starch films with edible films based on chitosan was also analysed.

2. MATERIALS AND METHODS

Hawaii papaya was bought in El Carmen, Ecuador. Control papayas (uncoated) were washed with water and disinfected with 0,01 % sodium hypochlorite. Afterwards, papayas were immersed in a water solution containing a fungicide (Tiabendazole and Imazalil). Papayas to be coated with edible films were washed with water and disinfected with sodium hypochlorite before applying the film containing solution. Papayas were immersed in the film containing solution and dried at 25 °C. Afterwards, papayas were stored for 28 days at 11 °C and a relative humidity (RH) between 70 and 80 % followed by 4 days at 25 °C and 60 % RH. Analyses were performed each week and 4 days after the storage at 25 °C.

Cassava starch (La Pradera, Ecuador) was bought in a local market in Manta, Ecuador. Chitosan, degree of deacetylation 95 % and Mw of 149 kDa, was donated by Universidad Pública de Navarra, Spain.

2.1 Film Preparation

Chitosan film was prepared by dissolving 1 % (w/v) of chitosan in 1 % (v/v) acetic acid solution. One percentage of Tween 20, 0,5 % (w/v) glycerol and 0,5 % (w/v) of glucose were added before the solution was homogenised by using an ultraturrax (Polytron, Switzerland) at 11000 rpm for 4 min.

Starch film was prepared by heating a 0,5 % (w/v) cassava starch suspension from room temperature (approx. 25 °C) up to 90 °C, where it was kept for 5 min. One percentage of Tween 20, 0,5 % (w/v) glycerol and 2 mmol/L of salicylic acid (when it was needed) were added before cooling (Table 1). Glucose (0,5 %, w/v), 0,15 % (w/v) cinnamaldehyde and 0,15 % (w/v) thymol (when they were needed) were added when the solution was at room temperature (Table 1). Afterwards, the solution was homogenised by using an ultraturrax (Polytron, Switzerland) at 11000 rpm for 4 min.

A multi-group design with four different treatments was used during the present work. The treatments were uncoated papayas and papayas coated with cassava starch + salicylic acid, cassava starch + cinnamaldehyde + thymol and papayas coated with chitosan. Weight loss, disease severity, texture analyses, soluble solids, titratable acidity and maturity index were measured in papayas stored for 28 days at 11 °C followed by 4 days at 25 °C.

2.2 Weight Loss

Weight loss was calculated by weighing the fruit at day zero and after each storage time. Measurements were performed in triplicate and the results were reported as percentage of weight

loss. After weighing, papayas were utilized for the remaining analyses.

Table 1. Composition of edible film containing solution

Treatment	CHI ² (%, w/v)	S ⁵ (%, w/v)	SA ⁶ (mmol/L)	C ⁷ (%, w/v)	T ⁸ (%, w/v)
UN ¹	-	-	-	-	-
CHI ²	1	-	-	-	-
SSA ³	-	0,5	2	-	-
SCT ⁴	-	0,5	-	0,15	0,15

¹Uncoated

²Chitosan

³Cassava starch + salicylic acid

⁴Cassava starch + cinnamaldehyde + thymol

⁵Cassava starch

⁶Salicylic acid

⁷Cinnamaldehyde

⁸Thymol

2.3 Disease Severity

Disease severity was determined according to Sivakumark et al., (2002). A visual analysis together with a scale from 1 to 5 was utilised, where 1 = 0 % of surface affected area, 2 ≤ 5 %, 3 = 5 – 20 %, 4 = 20 – 50 % and 5 ≥ 50 %.

2.4 Texture Analyses

Puncture tests were performed using the ends and the central part of the fruit. A Shimadzu texturometer (Model EZ-LX, Japan) together with a stainless steel probe of 3 mm diameter and 8 cm length were utilised. The probe was inserted 15 mm into the fruit at a speed of 10 mm/s and the maximum penetration force was recorded.

2.5 Soluble Solids

Half papaya was disintegrated by using a domestic blender. The disintegrated fruit was compressed manually and filtered with a textile. The juice obtained after compression was analysed by using a refractometer (Atago, Japan) according to AOAC (1990). The results were reported as °Brix.

2.6 Titratable Acidity

Titrate acidity was determined with 0.01 M NaOH according to AOAC (1990).

2.7 Maturity Index

Maturity index was determined according to Santamaría et al. (2009). A scale from 1 to 6 was utilised, where 1 corresponded to a green skin with a light yellow stripe; 2: green skin with a well-defined yellow stripe; 3: one or more orange-coloured stripes in the skin; 4: clearly orange-coloured skin with some light green areas; 5: characteristic orange-colour skin of papaya; 6: fruit colour similar to stage 5, but more intense.

2.8 Statistical analyses

Analysis of variance (ANOVA) and Tukey test ($p < 0.05$) were performed with IBM SPSS Statistics software.

3. RESULTS AND DISCUSSION

Figure 1 showed that papayas coated with starch + cinnamaldehyde+thymol (SCT) had the highest weight loss whereas samples coated with starch+ salicylic acid (SSA) had the lowest weight loss along the whole storage time. Statistical differences between SCT and SSA were found on day of storage 7, 14 and 21 (Table 2). No differences on weight loss between uncoated papayas and samples coated with chitosan were found along the whole storage time. Srivastava and Dwivedi (2000) found that salicylates delay the ripening of fruits, probably through inhibition of ethylene biosynthesis, and therefore maintain post-harvest quality. Salicylic acid as an electron donor produces free radicals which prevents normal respiration and therefore leads to low metabolic activity (Wolucka et al., 2005). Low metabolic activity may lead to lower weight loss (Sánchez-González et al., 2011).

Table 2 showed that soluble solids varied between 8,8 and 10,6 °Brix for all samples along the whole storage time. Acidity profile was the same for all samples. It decreased from 0,15 to 0,05 between the first and third week of storage. Afterwards, acidity remained constant up to the fourth week of storage and finally increased again. There was no statistical difference in soluble solids and acidity among coated and uncoated samples. The increase of acidity after the fourth week may be produced by the increase of storage temperature from 11 to 25 °C. Lechaudel et al. (2010) showed that variations in acid content in mango are due to changes in temperature and time during ripening.




Figure 1. Weight loss of Hawaii papaya coated with edible films and stored for 28 days at 11 °C followed by 4 days at 25 °C. ♦ uncoated, □ chitosan, ▲ starch+salicylic acid and × starch+cinnamaldehyde+thymol

Figure 2 showed that penetration force decreased for all samples along the whole storage time. Papayas coated with SCT showed the highest penetration force during the first two weeks of storage, being statistically different than other samples (Table 2). Papayas coated with SSA showed the highest penetration force between the third and fifth week of storage and was statistically different than other samples. The high reduction of penetration force on papayas coated with SCT after the second week could be due to volatilisation of essential oils. Absence of essential oil may lead to changes in

fruit texture. Ahmad et al. (2012) observed oregano essential oil evaporation during film formation. Acevedo-Fani et al. (2015) found absence of antibacterial effect of lemongrass essential oil against *E. coli* due to volatilisation of oil compounds during film formation.

According to the results of soluble solids and acidity (Table 2) no difference on maturity was found between uncoated samples and papayas coated with different edible films. In fact, results of maturity index (Figure 3) showed no differences among the samples up to the first week of storage. However from the second week, uncoated sample had a higher maturity index compared to coated papayas. No difference in maturity index was observed among papayas coated with chitosan, SSA and SCT along the whole storage time. Delay on fruit ripening was also found by Srivastava and Dwivedi (2000).

Table 2. Weight loss, soluble solids (°Brix), acidity, and maximum penetration force of Hawaii papaya coated with edible films and stored for 28 days at 11 °C followed by 4 days at 25 °C.

Day of storage	Treatment	WL ⁴ (%)	°Brix	A ⁵ (mL NaOH 0,01M)	PF ⁶ force (N)
0 ⁷	SCT ¹	0	9,83 ^a	0,13 ^a	9,20 ^a
	Chitosan	0	9,83 ^a	0,13 ^a	9,20 ^a
	UN ²	0	9,83 ^a	0,13 ^a	9,20 ^a
	SSA ³	0	9,83 ^a	0,13 ^a	9,20 ^a
7 ⁷	SCT ¹	0,06 ^a	10,07 ^a	0,15 ^a	7,17 ^a
	Chitosan	0,05 ^{a,b}	10,07 ^a	0,15 ^a	4,39 ^b
	UN ²	0,04 ^{a,b}	9,80 ^a	0,15 ^a	4,50 ^b
	SSA ³	0,04 ^b	9,47 ^a	0,15 ^a	5,15 ^b
14 ⁷	SCT ¹	0,11 ^a	10,0 ^a	0,08 ^a	6,71 ^a
	Chitosan	0,09 ^{a,b}	10,13 ^a	0,08 ^a	3,99 ^b
	UN ²	0,09 ^{a,b}	8,80 ^a	0,13 ^a	3,91 ^b
	SSA ³	0,08 ^b	9,93 ^a	0,07 ^a	4,82 ^b
21 ⁷	SCT ¹	0,16 ^a	10,5 ^a	0,08 ^a	2,20 ^b
	Chitosan	0,13 ^{a,b}	10,47 ^a	0,07 ^a	3,23 ^{a,b}
	UN ²	0,13 ^{a,b}	10,13 ^a	0,07 ^a	2,46 ^{a,b}
	SSA ³	0,11 ^b	9,43 ^a	0,08 ^a	3,52 ^a
28 ⁷	SCT ¹	0,21 ^a	10,0 ^a	0,05 ^a	2,09 ^d
	Chitosan	0,17 ^a	9,47 ^a	0,05 ^a	2,92 ^b
	UN ²	0,17 ^a	10,5 ^a	0,08 ^a	2,44 ^c
	SSA ³	0,15 ^a	10,17 ^a	0,05 ^a	3,80 ^a
32 ⁷	SCT ¹	0,31 ^a	10,6 ^a	0,08 ^a	1,66 ^c
	Chitosan	0,23 ^a	9,73 ^a	0,12 ^a	2,36 ^b
	UN ²	0,26 ^a	11,0 ^a	0,12 ^a	2,38 ^b
	SSA ³	0,21 ^a	9,67 ^a	0,08 ^a	3,12 ^a

¹ Starch + cinnamaldehyde + thymol

² Uncoated

³ Starch + salicylic acid

⁴ Weight loss

⁵ Acidity

⁶ Penetration force

⁷ For a day of storage, same superscript letters showed no statistical difference (p < 0,05)

Treatment of strawberry plants followed by post-harvest treatment of fruits with 2 mmol L⁻¹ salicylic acid effectively controlled the total decay and increased fruit shelf life (Babalar et al., 2007).




Figure 2. Penetration force of Hawaii papaya coated with edible films and stored for 28 days at 11 °C followed by 4 days at 25 °C. ♦ uncoated, □ chitosan, ▲ starch+salicylic acid and × starch+cinnamaldehyde+thymol




Figure 3. Maturity index of Hawaii papaya coated with edible films and stored for 28 days at 11 °C followed by 4 days at 25 °C. □ uncoated, ■ chitosan, ▨ starch+salicylic acid and ▩ starch+cinnamaldehyde+thymol

Uncoated samples showed a higher disease severity than samples coated with chitosan or SSA up to the third week of storage (Figure 4). Afterwards, the three samples showed similar results. Increase of storage temperature after the fourth week promoted fungi growth among all samples. Similar disease severity responses of uncoated papayas and samples coated with SCT suggested that physical mixture of starch, cinnamaldehyde and thymol may have a high releasing rate of both compounds during the first week of storage. A high releasing rate of cinnamaldehyde present in starch-cinnamaldehyde mixtures was found by Tian et al. (2013). Salicylic acid has been used to control fruit decay on pears during 5 months of cold storage (Asghari et al., 2007) whereas Qin et al. (2003) showed that salicylic acid significantly reduced the incidence of blue mould (*P. expansum*) and Alternaria rot (*A. alternata*) in sweet cherry. Regarding chitosan, Ruiz et al. (2010) reported that films based on chitosan and starch reduced the growing of mesophiles (4 Log

ufc/g) in fresh cut melon. The antimicrobial mechanism of chitosan was explained by Shahidi et al. (1999) as the action of the positive charges of amino group on the negative charges of the microorganism membrane cells.




Figure 4. Disease severity of Hawaii papaya coated with edible films and stored for 28 days at 11 °C followed by 4 days at 25 °C. □ uncoated, ■ chitosan, ▨ starch+salicylic acid and ▩ starch+cinnamaldehyde+thymol

4. CONCLUSION

The use of films based on cassava starch together with salicylic acid is a promising tool to preserve Hawaii papaya at refrigeration conditions. Moreover cassava starch films containing salicylic acid may replace the use of chitosan films for papaya preservation.

5. ACKNOWLEDGEMENTS

This research received funding from Universidad Laica Eloy Alfaro de Manabí, Ecuador

REFERENCES

- Abdou, E., Nagy, K., Elsabee, M. (2007). Edible films from essential-oil-loaded nanoemulsions: Physico-chemical characterization and antimicrobial properties. *Bioresour. Technol.* 99, 1359–1367.
- Acevedo-Fani, A., Salvia-Trujillo, L., Rojas-Graü, M., Martín-Belloso, O. (2015). Edible films from essential-oil-loaded nanoemulsions: Physico-chemical characterization and antimicrobial properties. *Food Hydrocolloids* 47, 168–177.
- Ahmad, M., Benjakul, S., Prodpran, T., Agustini, T. (2012). Physico-mechanical and antimicrobial properties of gelatin film from the skin of unicorn leatherjacket incorporated with essential oils. *Food Hydrocolloids* 28, 189–199.
- AOAC. (1990). *Official Methods of Analysis*. 15th ed. Association of Official Analytical Chemists Washington DC.
- Asghari, M., Hajitagilo, R., Shirzad, H. (2007). Postharvest treatment of salicylic acid effectively controls pear fruit diseases and disorders during cold storage. In: *Proceedings of the International Congress on Novel Approaches for the Control of Postharvest Diseases and Disorders*. COST action 924, 355–360.
- Asghari, R., Hajitagilo, R., Jalilimarandi, R. (2009). Postharvest application of salicylic acid before coating with chitosan affects the pattern of quality changes in table grape during cold storage. In: *6th International Postharvest Symposium*, Antalya, Turkey.
- Babalar, M., Asghari, M., Talaei, A., Khosroshahi, A. (2007). Effect of pre- and postharvest salicylic acid treatment on ethylene production, fungal decay and overall quality of Selva strawberry fruit. *Food Chemistry* 105, 449–453.
- Bezerra de Aquino, A., Fitzgerald, A., Lins de Aquino, L. (2015). Impact of edible chitosan-cassava starch coatings enriched with *Lippiagracilis*Schauer genotype mixtures on the shelf life of guavas (*Psidium guajava* L.) during storage at room temperature. *Food Chemistry* 171, 108–116.
- Burt, S. (2004). Essential oils: their antibacterial properties and potential applications in food. A review. *International Journal of Food Microbiology* 94, 223–253.
- Chiumarelli, M., Pereira, L., Ferrari, C., Sarantópoulos, C. (2010). Cassava starch coating and citric acid to preserve quality. *Journal of Food Science* 75, 297–304.
- Chiumarelli, M., Hubinger, M. (2012). Stability, solubility, mechanical and barrier properties of cassava starch-Carnauba wax edible coatings to preserve fresh-cut apples. *Food Hydrocolloids* 28, 59–67.
- Cia, P., Pascholati, S., Benato, E. (2007). Indução de resistência no manejo de doenças pós-colheita. P.245-280. In: Rodrigues, F., Romeiro, R. (Eds.), *Indução de resistência em plantas a patógenos*. Viçosa: UFV, pp. 245–280.
- Chinou, I., Liolios, C., Gortzi, O., Lalas, S., Tsaknis, J. (2009). Liposomal incorporation of carvacrol and thymol isolated from the essential oil of *Origanum dictamnus* L. and in vitro antimicrobial activity. *Food Chem.* 112, 77–83.
- Chivrac, F., Angellier-Coussy, H., Guillard, V., Pollet, E., Avérous, L. (2010). How does water diffuse in starch/montmorillonite nanobiocompositematerials. *Carbohydrate Polymers* 82, 128–135.
- De Souza, A., Dias, A., Sousa, H., Tadini, C. (2014). Impregnation of cinnamaldehyde into cassava starch biocomposite films using supercritical fluid technology for the development of food active packaging. *Carbohydrate Polymers*, 102, 830–837.
- Durango, A., Soares, N., Andrade, N. (2006). Microbiological evaluation of an edible antimicrobial coating on minimally processed carrots. *Food Control* 17, 336–341.
- El-Mougy. (2002). In vitro Studies on Antimicrobial Activity of Salicylic Acid and Acetylsalicylic Acid as pesticidal Alternatives Against some Soilborne Plant Pathogens. *Egypt Journal Phytopathology* 30, 41–55.
- Kessmann, H., Staub, T., Hofmann, C., Maetzke, T., Herzog, J. (1994). Induction of systemic acquired disease resistance in plants by chemicals. *Annual Review of Phytopathology* 32, 439–59.
- Lechaudel, M., Uan L., Joas, J. (2010). Chlorophyll fluorescence, a nondestructive method to assess maturity of mango fruits (Cv. ‘Cogshall’) without growth conditions bias. *J. Agric Food Chem.* 14, 7532–7538.
- Mastromatteo, M., Barbuzzi, G., Conte, A. (2009). Controlled release of thymol from zein based film. *Innovative Food Science & Emerging Technologies* 10, 222–227.
- Meng, X., Li, B., Liu, J., Tian, S. (2008). Physiological responses and quality attributes of table grape fruit to chitosan preharvest spray and postharvest coating during storage. *Food Chem.* 106, 501–508.
- OECD/Food and Agriculture Organization of the United Nations (2015), *OECD-FAO Agricultural Outlook 2015*, OECD Publishing, Paris.

Pan, K., Chen, H., Davidson, P., Zhong, Q. (2014). Thymol nanoencapsulated by sodium caseinate: physical and anti-listerial properties. *J. Agric. Food Chem.* 62, 1649–1657.

Pauli, A., H. Schilcher. (2010). In vitro antimicrobial activities of essential oils monographed in the European Pharmacopoeia, in: Baser, K., Buchbauer, G. (Eds.), *Handbook of Essential Oils – Science, Technology, and Applications*. CRC Press, Boca Raton, FL, pp. 353-548.

Qin, Q. Z., Tian, S., Xu, Y., Wan, Y. (2003). Enhancement of biocontrol efficacy of antagonistic yeasts by salicylic acid in sweet cherry fruit. *Physiological and Molecular Plant Pathology* 62, 147-154.

Raskin, I. (1992). Role of salicylic acid in plants. *Annual Review of Plant Physiology and Plant Molecular Biology* 43, 439-463.

Raybaudi, R., Mosqueda, J., Martín, O. (2006). Antimicrobial activity of essential oils on *Salmonella* Enteritidis, *Escherichia coli*, and *Listeria innocua* in fruit juices. *Journal of Food Protection* 69, 1579 - 1586.

Ribeiro, C., Vicente, A., Teixeira, J., Miranda, C. (2007). Optimization of edible coating composition to retard strawberry fruit senescence. *Postharvest Biology and Technology* 44, 63–70.

Ruiz, S., Guevara, C., Estrada, I., Cira, L., Gassós, L., Llana, A. (2010). Aplicación de películas comestibles a base de quitosano y almidón para mantener la calidad sensorial y microbiológica de melón fresco cortado. *Revista Internacional de Ciencia y Tecnología Biomédica* 1, 1-10.

Sanchez-Gonzalez, L., Pastor, C., Vargas, M., Chiralt, A., Gonzalez-Martinez, C. and Chafer, M. (2011). Effect of Hydroxypropylmethylcellulose and Chitosan Coatings with and without Bergamot Essential Oil on Quality and Safety of Coldstored Grapes. *Postharvest Biol. Technol.*, 60: 57–63.

Santamaría, F., Basulto, E., Duch, S., Espadas, F., Gil, Díaz R., Larqué, A., Saavedra, J., (2009). Postharvest ripening and maturity indices for maradol papaya. *Interciencia* 34, 583- 588.

Shahidi, F., Arachchi, J. Jeon, Y. (1999). Food applications of chitin and chitosans. *Trends in Food Science & Technology* 10, 37-51.

Sivakumark, D., Hewarathgamagae, R., Wijeratnam, W., Wijesundera W. (2002). Effect of ammonium carbonate and sodium bicarbonate on anthracnose of papaya. *Phytoparasitica*, 30, 486-492.

Souza, A., Benze, R., Ferrão, E., Ditchfield, C., Coelho, A., Tadini, C. (2012). Cassava starch biodegradable films: Influence of glycerol and clay nanoparticle content on tensile and barrier properties and glass transition temperature. *LWT - Food Science and Technology* 46, 110-117.

Srivastava, M., Dwivedi, U. N. (2000). Delayed ripening of banana fruit by salicylic acid. *Plant Science* 158, 87-96.

Vargas, M., C. Pastor, A. Chiralt, D. J. McClements y C. González-Martínez. (2008). Recent advances in edible coatings for fresh and minimally processed fruits. *Critical Reviews in Food Science and Nutrition* 48(6): 496-511.

Wolucka, B., Goossens, A., Inze, D. (2005). Methyl jasmonate stimulates the de novo biosynthesis of vitamin C in plant cell suspensions. *J. Exp. Bot.* 56, 2527–2538.

Yao, H., Tian, S. (2005). Effects of pre- and post-harvest application of salicylic acid or methyl jasmonate on inducing disease resistance of sweet cherry fruit in storage. *Postharvest Biology and Technology* 35, 253-262.

Zhang, Y., Zhang, M., Yang, H. (2015). Postharvest chitosan-g-salicylic acid application alleviates chilling injury and preserves cucumber fruit quality during cold storage. *Food Chemistry* 174, 558-563



Marlon Castro, graduado de Ingeniero Agroindustrial en la Universidad Laica Eloy Alfaro de Manabí y actualmente se desempeña como asistente de investigación en la misma institución.



María Isabel Mantuano, graduado de ingeniera agroindustrial de la Escuela Superior Politécnica Agropecuaria de Manabí, realizó su Maestría en Procesamiento de Alimentos en la Universidad Agraria del Ecuador y actualmente labora como docente en la Universidad Laica Eloy Alfaro de Manabí



José Luis Coloma, graduado como Ingeniero de Alimentos de la Escuela Politécnica del Litoral se desempeñó en algunas empresas privadas vinculadas a la producción de alimentos. Realizó su Maestría en Procesamiento de Alimentos en la Universidad Agraria del Ecuador y actualmente labora como docente en la Universidad Laica Eloy Alfaro de Manabí



Stalin Santacruz. Graduado como Ingeniero Químico en la Escuela Politécnica Nacional, luego de lo cual se desempeñó como asistente de investigación en el entonces Instituto de investigaciones Tecnológicas (actual DECAB). Realizó su maestría en la misma institución, y luego de ello trabajó como investigador en North East Wales Institute (UK). Seguidamente hizo sus estudios de doctorado en Swedish University of Agricultural Sciences, Suecia y en Lund University el postdoctorado. De regreso al Ecuador trabajó como docente en la Universidad San Francisco de Quito y actualmente labora como docente-investigador en la Universidad Laica Eloy Alfaro de Manabí.